



Tackwhite HT 200 NC M

Description

TACKWHITE HT 200 NC M is a waterborne pressure sensitive adhesive, based on acrylic polymers modified with acrylic plasticizers.

It yields a transparent film with very high cohesion, medium-high adhesion and elevated thermal resistance.

Application

TACKWHITE HT 200 NC M, thanks to its outstanding shear properties, can be used for semi-permanent labels, double sided adhesive tapes, melamine plastics, wood, metals, glass, ceramic, where tapes must be removed without adhesive transfer on the contact surface. To get a very good heat resistance (over 150°C), it is necessary to cure the product with isocyanate (e.g. CURING AGENT W 3 DIL.), polyaziridine (e.g. CURING AGENT X7), ... The crosslinker has to be added just before use and has to be well mixed into the adhesive. After activation, pot life decreases depending on adhesive concentration, amount of crosslinker, temperature; we recommend to run preliminary laboratory tests to evaluate the right amount of crosslinker.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	50±1
3. Brookfield Viscosity 25°C	mPa.s	100 - 1000 ⁽¹⁾
8. pH Solvents	pH	8 - 10 water

⁽¹⁾ N. 2 RV; 20 RPM

Film properties

Method of analysis	MU	Standard
10. Peel Adhesion on Steel	N/in	9
22. Static Shear	h	> 100
125. Loop Tack	N	10

Average values; 22±2 g/m² of dry adhesive on PET film 36 µm

Handling

TACKWHITE HT 200 NC M is ready for application by Mayer bar, reverse roll or air knife coating systems; higher viscosity versions can be supplied on request for rotating blade or direct knife coating systems.

If necessary, it can be diluted with water.

Packaging

The product is supplied in iron drums (200 kg); IBC containers (1000 kg).

Storing

Product must be stored at temperatures between +5°C and +40°C. Protect from freezing. In case of prolonged storage, stir well before use.

Use within 6 months from production date (unopened and in the original packaging).