Blendex S 24/20 M1

Description

BLENDEX S 24/ 20 M1 is a MEK solution of a thermoplastic polyurethane. After drying, the film is matt.

Application

BLENDEX S 24/ 20 M1 is used as soft heat sealable adhesive for lamination of various products, like PU, PVC, TR, leather, synthetic leather and fabrics.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	21.5±1.50
3. Brookfield Viscosity 25°C	mPa.s	6000 - 12000 (1)
95. Heat Sealability	°C	70
Solvents		MEK

(1) N. 5 RV; 20 RPM

Handling

Reactivation temperature: over 70°C.
After reactivation, the product has good adhesive properties for a quite long time. (open time: long).

Packaging

The product is supplied in iron drums (170 kg).

Storing

Stir well before use. Keep containers well closed to prevent solvent evaporation. Store at temperatures between + 5 and + 30°C, far from heat sources and direct sunglight.

Use within 12 months from production date (unopened and in the original packaging).

Build date 11 Sep 2025

Above information is reliable, but does not constitute warranty.

ICHEMCO srl
via 11 Settembre, 5 - 20012 CUGGIONO (MI) - ITALY
Phone: +39 02 97243.1 - info@ichemco.it - www.ichemco.it