ichemco
Developing Chemical Excellence

CERTIFIED MANAGEMENT SYSTEMS
CERTIQUALITY
UNI EN ISO **9001:2015**
UNI EN ISO **14001:2015**
UNI ISO **45001:2018**

Tackmelt 44 B

(Provisional)

Description

TACKMELT 44 B is a hot-melt adhesive based on thermoplastic elastomers (SIS) and synthetic resins.
Special synergic antioxidants are added to guarantee the best ageing resistance.
It has very good tack and peel adhesion and a moderate cohesion.

Application

It can be used at medium-low temperatures to different products such as foams, synthetic leathers, fabrics, non-wovens and similar.

Technical Specifications

Method of analysis	MU	Standard
4. Softening Point, Ring & Ball	°C	65 - 85
108. Viscosity at 170°C	mPa.s	3000 - 9000 (1)

(1) Brookfield viscometer, No 27 RV

Handling

TACKMELT 44 B must be heated at 150-170°C with a suitable heating equipment and kept at a set stable temperature while coating (temperature changes cause a variation of the viscosity and, consequently, of the processing condition).
The best coating system is slot-die.
The product has been designed to withstand high temperatures, but it is preferable to avoid thermal shocks.

Packaging

The product is supplied in 150g pillows packed in cardboard boxes (20 kg); fibre drums (180 kg).

Storing

Keep the product at temperatures lower than +25°C. Avoid contact with dust and liquids. Keep far from heat sources and direct sunlight.

Use within 12 months from production date (unopened and in the original packaging).

Notes

The product, once coated, is subject to oxidation from air and light and must be protected in order not to compromise its performance.

Shelf life of TACKMELT 44 B packed in pillows is 3 months. Shelf life of TACKMELT 44 B packed in fibre drums (180 kg) is 12 months.

Build date 11 Sep 2025

Above information is reliable, but does not constitute warranty.

ICHEMCO srl
via 11 Settembre, 5 - 20012 CUGGIONO (MI) - ITALY
Phone: +39 02 97243.1 - info@ichemco.it - www.ichemco.it